

Product	Features	Solids Weight (Approx.)	Flash Point (Closed Cup)	Consistency	Color Dry Film	Application Method	Bonding Range	Overlap Shear Strength (PSI)		Peel Strength (PIW)
								75°F (24°C)	180°F (82°C)	75°F (24°C)
Scotch-Grip Contact Adhesives	5	19%	-14°F (-26°C)	Thin liquid	Green, Light Yellow	Spray	30 minutes minimum	482 ⁽¹⁾	65 ⁽¹⁾	19 ⁽²⁾
	10	22%	-14°F (-26°C)	Thin liquid	Light Yellow	Brush, roller	30 minutes minimum	482 ⁽¹⁾	65 ⁽¹⁾	19 ⁽²⁾
	1357	25%	-14°F (-26°C)	Thin liquid	Gray-green, Light Yellow	Brush, spray	30 minutes minimum	536 ⁽¹⁾	199 ⁽¹⁾	42 ⁽²⁾
	1357-L	18%	-14°F (-26°C)	Thin liquid	Gray-green	Spray	30 minutes minimum	536 ⁽¹⁾	199 ⁽¹⁾	42 ⁽²⁾

Note: The technical information and data on these pages should be considered representative or typical only, and should not be used for specification purposes.

- (1) Birch plywood to birch plywood @ 0.1 inches/minute separation rate.
- (2) Canvas to cold rolled steel @ 2.0 inches/minute separation rate.

Note: Flash Point (closed cup) in all Fastbond Adhesives: None.



Note: 3M[®] Hi-Strength 90 Adhesive, a popular 3M aerosol adhesive (see page 25), is now also available in bulk form.