

	Viscosity CPS ⁽²⁾	Delivery Time (sec) for 1" x 3" Cartridge**	Ball & Ring Soft Point ⁽³⁾ (°F/°C)	Heat Resistance (°F/°C)	Impact Resistance (in. -lbs.) 72°F (22°C)	Peel Strength PIW ⁽⁴⁾ 72°F (22°C)	Shear Strength PSI ⁽⁵⁾ 72°F (22°C)	Tensile Strength PSI 72°F (22°C)	Elongation %	Bonding Range 1/8" Bead (sec) ⁽⁶⁾
	13,000 @250°F	N/A	157/70	120/49	14	13	500	380	400	120
	4000 @250°F	45	205/96	130/54	13	6	480	600	300	25
	8250 @250°F	47	184/84	140/60	13	9	600	270	600	40
	10,500 @250°F	57	178/81	140/60	62	13	350	547	125	40
	9500 @250°F	N/A	191/88	120/49	N/A	N/A	N/A	62	250	30
	2875 @375°F	35	186/86	130/54	36	13	375	360	1000	50
	4100 @375°F	45	220/104	145/63	25	20	430	750	1300	45
	5000 @375°F	65	292/144	175/79	24	18	250	375	1100	45
	5500 @375°F	65	305/152	175/79	50	15	275	200	1850	30
	1870 @375°F	30	201/94	130/54	20	7	545	450	400	35
	6000 @375°F	55	190/88	140/60	58	14	390	650	625	40
	7000 @375°F	75	325/163	300/149	22	18	700	2100	300	25
	5200 @375°F	70	270/132	220/104	40	16	570	520	600	50
	5000 @375°F	45	179/81	140/60	42	13	250	400	750	50
	23,000 @375°F	120	240/116	200/93	29	29	550	363	930	40
	2650 @375°F	55	304/151	170/77	19	10	350	283	98	30
	3500 @300°F	57	196/91	<100/38	N/A	N/A	N/A	N/A	N/A	50
	15,000 @325°F	N/A	224/107	120/49	N/A	16	N/A	N/A	N/A	> 60
	18,000 @325°F	N/A	260/127	170/77	N/A	14	N/A	N/A	N/A	> 60

* Also available in bulk.

** Time to deliver the third consecutive cartridge through PG II or PG II LT @ 80 PSI.

N/A = Not available